

## Description

Soft PVC film available both with glossy or matt surface.

## Release paper

Silicone coated paper on one side, 137 g/m<sup>2</sup>, which provides excellent waste-stripping properties. For white vinyl a light blue silicone paper is used to form a stronger contrast to lettering.

## Adhesive

Polyacrylate, permanent

## Area of use

Very good suitable for the use on cutting plotter systems for the production of short- and medium-term markings, inscriptions and decorations to be applied outdoors. Indoor exposure is almost unlimited. Glossy surface is additionally suitable for thermal transfer printing (with resin ribbons).

## Technical data

<b>Thickness*</b> (without protective paper and adhesive)	75 micron
<b>Dimensional stability</b> (FINAT TM 14)	adhered to steel, no measurable shrinkage in cross direction, in length 0.4 mm max.
<b>Temperature resistance</b>	adhered to aluminium, -40°C to +80°C, no variation
<b>Water resistance</b>	adhered to aluminium, after 48h/23°C no variation
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	16 N/25 mm
<b>Tensile strength</b> (DIN EN ISO 527)	
along	min. 19 MPa
across	min. 19 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	
along	min. 130%
across	min. 150%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	min. +10°C
<b>Service life by specialist application</b> under vertical outdoor exposure (normal climate of Central Europe)	black / white: 4 years transparent / coloured: 3 years metallic: 3 years

\* average      \*\* in original packaging, at 20°C and 50% relative humidity

## Attention:

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application informations published by ORAFOL are to be considered.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.

